



**NOTES**

1. ALL SURVEY MARKERS SHALL BE CENTER PUNCHED AFTER PLACEMENT.
2. 1-1/2" MINIMUM DIAMETER ALUM. OR BRASS CAP W/PLS# PERMANENTLY ATTACHED PRIOR TO PLACEMENT.
3. MONUMENT POT SHALL BE SET 3/8"-5/8" BELOW FINISHED ROADWAY SURFACE.
4. CONC COLLAR SHALL BE LEFT 2" BELOW FINISHED ASPH SURFACE. TOP OF CONC SHALL RECEIVE A ROUGH BROOM FINISH. PLACE 2" OF TYPE 3 ASPH AROUND MONUMENT POT. APPLY SS-1 TACK COAT TO TOP OF CONC BEFORE PLACING ASPH PAVING, & SEAL ASPH SURFACE W/SS-1 TACK COAT & SAND. CHIP SEAL, SAND SEAL, SLURRY SEAL OR FOG SEAL PAVED SURFACE AS REQ'D BY PLANS OR SPECS.
5. CONC SHALL BE FLUSH W/TOP OF SURVEY POT WHEN NOT LOCATED IN ASPH PAVING.
6. TYPE A, TYPE B OR TYPE C PIN MAY BE USED. SEE SHEET W-18.1 FOR TYPE A AND B PINS.
7. CONCRETE SHALL BE MIN. 6.25SACKS OF TYPE II CEMENT (588lbs) PER CU. YD OF CONCRETE - 4000 psi COMPRESSIVE STRENGTH @ 28 DAYS WITH 4.5 - 7.5% AIR

NO.	REVISION	DATE	STANDARD DETAILS FOR PUBLIC WORKS CONSTRUCTION	SECTION	
1	<b>REDRAW</b>	10/09sw	MONUMENTS	WASHOE	
2	Added pins	3/10 sw		DRAWING NO.	
3	Note 7	12/11sw		W-18	
4				DATE <b>03/10sw</b>	PAGE <b>34</b>