



TYP. SEC.

N.T.S.

NOTES

1. PORTLAND CEMENT CONC (PCC) SHALL BE MIN 4000 psi COMPRESSIVE STRENGTH @ 28 DAYS W/MIN 6.25 sacks OF TYPE II CEMENT (588 lbs) PER CU.YD., 4.5-7.5% AIR, MAX 4" SLUMP. REINFORCING SHALL CONSIST OF COLLATED FIBRILLATED POLYPROPYLENE FIBERS AS MFD BY FIBERMESH OR APPROVED EQUAL. ALL MATERIALS SHALL CONFORM TO SSPWC SEC.202.
2. TRANSVERSE/LONGITUDINAL CRACK CONTROL JOINTS SHALL BE PLACED ON 5 FOOT[±] CENTERS.
3. SUBGRADE SOILS SHALL BE OVEREXCAVATED IN AREAS OF UNSTABLE OR EXPANSIVE SOILS TO CONFORM W/SOILS REPORT OR WASHOE COUNTY REQUIREMENTS.
4. CONC SHALL RECEIVE A MEDIUM BROOM FINISH.
5. CURING AGENTS SHALL BE APPLIED PER SEC.202.11.02 IMMEDIATELY AFTER FINAL FINISHING.

NO.	REVISED	DATE	STANDARD DETAILS FOR PUBLIC WORKS CONSTRUCTION BUS TURNOUT • STRUCTURAL	SECTION:	WASHOE
1	Note 1	12/11sw		DRAWING NO:	W-8.2
				DATE:	8/94 vp
				PAGE:	20